Endura Kolormax

TECHNICAL DATASHEET

www.ja-int.com

APPLICATION

Temperature (°C):	190°C	
Temperature (°F):	374°F	
Time:	12 seconds	
Pressure:	High	56.9 - 71.1 psi / 3.9 - 4.9 bar / 4.0 - 5.0 kg/cm2
Carrier Release:	Instant/Hot peel	

LAUNDERING
Suitable for Industrial Laundering up to 85°C
Suitable for Industrial Drying Techniques - Medium
Suitable for Dry-Cleaning
Iron - Medium, On Reverse
Do Not Bleach
Do Not wash with strong Acid or Alkaline additives

HANDLING AND STORAGE
Store in a damp-free environment at a stable temperature of ~20°C
Keep away from direct sunlight
No personal protection equipment is required in handling and storage
Do not attempt to apply any transfer that has been removed from its carrier

COMPOSITION
Ink - Digital & Water Based
Adhesive - Polyester
Carrier - Coated Polyester Sheeting

HEALTH & SAFETY
This product is identified as Non-Hazardous to the end user
No PPE is required during application**

ENVIRONMENTAL / RECYCLING
All inks are compostable
Polyester carrier - non-recylable
Vegan-Friendly: No

CERTIFICATION
Wash Stability: EN ISO 15797

**Any fumes created by this transfer during application are harmless. However, modern garment materials can be coated and finished in many different ways; some of which may alter their application and health & safety requirements. We recommend thorough checking and testing of any garment material to determine the correct requirements before application.